

Product Information

Cryolite Patinal®

GENERAL INFORMATION

Cryolite (Na_3AlF_6) forms highly transparent, but soft and slightly hygroscopic layers. Thanks to its extended range of transparency it can be used for coatings from the UV to the IR wavelength range.

AREAS OF APPLICATION

- Multilayer coatings, e.g. interference filters with ZnS and Cryolite

THIN FILM PROPERTIES

Range of transparency	200 nm – 14 μm
Refractive index at 500 nm	1.32 – 1.35
Thin film stress	Tensile

The resulting optical properties of the thin film are dependent on process conditions like deposition rate and substrate temperature.

NOTES FOR EVAPORATION

Evaporator source	Resistance heater thermal evaporator
Boat	Molybdenum or tantalum indirectly heated alumina crucibles
Evaporation temperature	800 - 1200 °C
Deposition rate	0.8 – 2.0 nm/s
Substrate temperature	250 – 300 °C
QCR-settings	Density 2.90 g/cm ³ , z-ratio 1.0

Cryolite decomposes to AlF_3 and NaF during evaporation. The composition of the deposited layer varies depending on evaporation temperature. It is of advantage to evaporate at a pressure of less than 2×10^{-5} mbar and to use a liquid nitrogen cooled baffle.



PRODUCTS

Cryolite Patinal® is available as granules.

Product Code	Description	Purity*	Dimensions
1.06457	Cryolite Patinal®	≥ 99.95 % (3N5)	Granules, about 1-4 mm

* The purity values are based on the specified trace metals.

Appearance

1.06457	White granules
---------	----------------

SPECIFICATION

Cobalt (Co)	≤ 0.001 %	Sizes	
Copper (Cu)	≤ 0.001 %	1.06457	granules 1- 4 mm
Chromium (Cr)	≤ 0.002 %		≥ 80 %
Iron (Fe)	≤ 0.005 %	Application test	
Vanadium (V)	≤ 0.005 %	Each batch has to pass a specific application test assessing its evaporation behaviour.	
Oxygen (O)	≤ 1.0 %		

RoHS information

The RoHS compliance information is part of the Certificate of Analysis (CoA) for each batch of Patinal® material.



Quality assurance

Research, production and sales of our Patinal® evaporation materials take place under a certified DIN EN ISO 9001:2000 quality management system and DIN EN ISO 14001 environmental management system. The quality of the materials is assured by our manufacturing processes, in-process controls and quality tests. Each batch is released only after passing our chemical analysis and application tests designed to confirm the suitability of the material for the evaporation process.

Handling precautions

Product safety information required for safe use is not included in this document. Before handling, read product and safety sheets and container labels for safe use, physical and health hazard information. The material safety data sheet is available online at www.patinal.com, from your EMD representative or distributor, or by calling your global Merck KGaA, Darmstadt, Germany, contact.

Disclaimer

Products are warranted to meet the specifications set forth on their label/packaging and/or certificate of analysis at the time of shipment or for the expressly stated duration. EMD MAKES NO REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE REGARDING OUR PRODUCTS OR ANY INFORMATION PROVIDED IN CONNECTION THEREWITH. Customer is responsible for and must independently determine suitability of EMD's products for customer's products, intended use and processes, including the non-infringement of any third parties' intellectual property rights. EMD shall not in any event be liable for incidental, consequential, indirect, exemplary or special damages of any kind resulting from any use or failure of the products: All sales are subject to EMD's complete Terms and Conditions of Sale. Prices are subject to change without notice. EMD reserves the right to discontinue products without prior notice.

EMD, EMD Performance Materials, the vibrant M, Patinal are trademarks of Merck KGaA, Darmstadt, Germany.

